

L. Soliev, M. T. Jumaev, R. O. Turaev,  
H. R. Makhmadov, B. B. Dzabborov*Tajik State Pedagogical University named after S. Ayni*  
121 Prospect Rudaki, Dushanbe, 734003, Tajikistan  
E-mail: Soliev.Lutfullo@yandex.com; jumaev\_m@bk.ru

## Structure of the solubility diagram in the $\text{Na}_2\text{SO}_4\text{-Na}_2\text{CO}_3\text{-NaHCO}_3\text{-H}_2\text{O}$ system AT 0, 25 and 50 °C

The solubilities in invariant points of  $\text{Na}_2\text{SO}_4\text{-Na}_2\text{CO}_3\text{-NaHCO}_3\text{-H}_2\text{O}$  system were investigated at 0, 25 and 50 °C. The phase equilibria in the said system were discussed, and phase diagrams at given temperatures were constructed.

**Keywords:** solubility, phase equilibria, liquid phase, chemical analysis, crystallo-optical analysis, phase diagram

Received: 07.07.2018. Accepted: 23.07.2018. Published: 30.07.2018.

© Soliev L., Jumaev M. T., Turaev R. O., Makhmadov H. R., Dzabborov B. B., 2018

### Introduction

Four-component system  $\text{Na}_2\text{SO}_4\text{-Na}_2\text{CO}_3\text{-NaHCO}_3\text{-H}_2\text{O}$  is a part of more complex six-component system Na, Ca// $\text{SO}_4, \text{CO}_3, \text{HCO}_3, \text{F-H}_2\text{O}$ . Equilibria in the latter determine the conditions of aluminium production liquid waste disposal. The waste water of cryolite recycling plants contains fluorides, carbonates, bicarbonates and sulphates of sodium and calcium [1, 2]. Crystallization and dissolution processes in such waste water are governed by the phase equilibria both in six-component system Na, Ca// $\text{SO}_4, \text{CO}_3, \text{HCO}_3, \text{F-H}_2\text{O}$

and in its constituents, five- and four-component systems.

In our earlier studies [3, 4] the phase diagrams in similar systems were constructed. This study presents the results of investigation of  $\text{Na}_2\text{SO}_4\text{-Na}_2\text{CO}_3\text{-NaHCO}_3\text{-H}_2\text{O}$  system at 0, 25 and 50 °C using solubility method. The main goal of this work was to establish the concentration parameters of geometrical images and separation of the crystallization fields of individual equilibrium solids in the phase diagrams.

### Results and discussion

The system investigated contains the following equilibrium solid phases: Nk – nahcolite  $\text{NaHCO}_3$  (0, 25, 50 °C); Mb – mirabilite  $\text{Na}_2\text{SO}_4 \cdot 10\text{H}_2\text{O}$ , C-10 –  $\text{Na}_2\text{CO}_3 \cdot 10\text{H}_2\text{O}$  (0, 25 °C); Tr – throne  $\text{NaHCO}_3 \cdot \text{Na}_2\text{CO}_3 \cdot 2\text{H}_2\text{O}$  (25, 50 °C); Th – thenardite  $\text{Na}_2\text{SO}_4$ , Bur – burkeite  $2\text{Na}_2\text{SO}_4 \cdot \text{Na}_2\text{CO}_3$ , C-1 –  $\text{Na}_2\text{CO}_3 \cdot \text{H}_2\text{O}$  (50 °C) [5, 6].

The following reagents were used in experiments:  $\text{Na}_2\text{SO}_4 \cdot 10\text{H}_2\text{O}$  (“chemically pure” grade),  $\text{Na}_2\text{CO}_3$  (“pure” grade),  $\text{NaHCO}_3$  (“pure” grade). The experiments were carried out according to “saturation method” described in detail elsewhere [8].

Based on the data available [5, 6], we prepared the mixtures of precipitates with saturated solutions according to the invari-




Fig. 1. Micrographs of equilibrium solid phases, corresponding to the invariant points of system  $\text{Na}_2\text{SO}_4\text{-Na}_2\text{CO}_3\text{-NaHCO}_3\text{-H}_2\text{O}$  at 0 (1, 2, 3, 8), 25 (1, 2, 3, 4, 9, 10) and 50 (2, 4, 5, 6, 7, 11, 12, 13) °C

ant points in the three-component systems  $\text{Na}_2\text{SO}_4\text{-Na}_2\text{CO}_3\text{-H}_2\text{O}$ ,  $\text{Na}_2\text{SO}_4\text{-NaHCO}_3\text{-H}_2\text{O}$  and  $\text{Na}_2\text{CO}_3\text{-NaHCO}_3\text{-H}_2\text{O}$  at 0, 25 and 50 °C. Then, transferring the non-variant points from the three-component section to the four-component section [3, 4], the saturated solutions prepared had been kept in a thermostat at a given temperature until the equilibrium was reached.

Thermostating was carried out in U-8 ultra-thermostat. Stirring was performed using a PD-09 magnetic stirrer for 50–120 h. Temperature was maintained with 0.1 °C accuracy using a contact thermo-

meter. Crystallization of solid phases was observed with a POLAM-R 311 microscope. After the equilibrium in a given system was achieved, the solid phases were photographed with a Sony-DSC-S500 digital camera. Equilibrium was assumed to be attained when the phase composition of the precipitates was constant.

A Buchner funnel with an ash-free filter paper (Blue Band) connected to a vacuum pump has been used for separation of the liquid phase and solid phase. The precipitate after filtration was washed with 96% ethanol and then dried at 120 °C. The

Table 1  
Solubility in central (invariant) points in system  $\text{Na}_2\text{SO}_4\text{-Na}_2\text{CO}_3\text{-NaHCO}_3\text{-H}_2\text{O}$

№ of points	Structure of a liquid phase, mas. %				Phase composition of deposits
	$\text{Na}_2\text{SO}_4$	$\text{Na}_2\text{CO}_3$	$\text{NaHCO}_3$	$\text{H}_2\text{O}$	
0 °C					
$E_1^3$	2.73	–	5.58	91.69	Mb+Nk
$E_2^3$	–	5.6	4.6	89.8	Nk+ C·10
$E_3^3$	2.8	6.0	–	91.2	C·10+Mb
$E_1^4$	2.12	5.13	4.37	88.38	Mb+Nk+C·10
25 °C					
$E_1^3$	16.4	18.3	–	65.3	Mb+C·10
$E_2^3$	20.68	–	4.16	75.16	Nk+Mb
$E_3^3$	–	17.62	4.62	77.76	Tr+Nk
$E_4^3$	–	22.46	2.84	74.7	C·10+Tr
$E_1^4$	21.2	20.07	5.51	50.22	Mb+Tr+C·10
$E_2^4$	20.9	22.54	4.77	50.68	Nk+Tr+Mb
50 °C					
$E_1^3$	29.65	–	4.05	66.30	Th+Nk
$E_2^3$	22.47	10.52	–	67.61	Th+Bur
$E_3^3$	5.87	28.52	–	65.61	Bur+C·1
$E_4^3$	–	16.92	6.30	76.78	Nk+Tr
$E_5^3$	–	31.80	0.85	67.35	Tr+C·1
$E_1^4$	12.64	21.31	2.51	54.76	Th+Nk+Bur
$E_2^4$	4.30	24.36	0.64	58.03	Bur+Tr+C·1
$E_3^4$	7.52	9.14	3.24	60.08	Tr+Nk+Bur

standard techniques used for the chemical analysis of products are described elsewhere [8–10].

Results of the crystalloptical analysis [11] of equilibrium solid phases (microphoto) are presented in Fig. 1, and the results of the chemical analysis of the saturated solutions are given in Table 1.

On the basis of the data obtained, the diagrams of solubility in the  $\text{Na}_2\text{SO}_4$ - $\text{Na}_2\text{CO}_3$ - $\text{NaHCO}_3$ - $\text{H}_2\text{O}$  system at 0, 25 and 50 °C were constructed. Salt parts of these diagrams are shown in Fig. 2. The location of non-variant points on the diagrams were determined by the center of mass method [12].




Fig. 2. Solubility diagrams in  $\text{Na}_2\text{SO}_4$ - $\text{Na}_2\text{CO}_3$ - $\text{NaHCO}_3$ - $\text{H}_2\text{O}$  system: a – at 0 °C; b – at 25 °C; c – at 50 °C

## References

1. Morozova VA, Rzhechitskii EP. [Solubility in the NaF – Na<sub>2</sub>SO<sub>4</sub> – NaHCO<sub>3</sub> – H<sub>2</sub>O system at 0 °C]. *Zhurnal Prikladnoi Khimii [Journal of Applied Chemistry]*. 1976;49(5):1152–4. Russian.
2. Morozova VA, Rzhechitskii EP. [Solubility in the systems NaF – NaHCO<sub>3</sub> – H<sub>2</sub>O, NaF – Na<sub>2</sub>SO<sub>3</sub> – H<sub>2</sub>O and NaF – Na<sub>2</sub>CO<sub>3</sub> – H<sub>2</sub>O at 0 °C]. *Zhurnal Neorganicheskoi Khimii [Russ J Inorg Chem]*. 1977;22(3):873–4. Russian.
3. Soliev L, Tursunbadalov Sh. Phase equilibria in the Na, K||SO<sub>4</sub>, CO<sub>3</sub>, HCO<sub>3</sub>-H<sub>2</sub>O system at 25°C. *Russ J Inorg Chem*. 2008;53(5):805–11.
4. Soliev L, Dzhumaev MT, Turaev RO. Fazovye ravnovesiya sistemy Na<sub>2</sub>SO<sub>4</sub>-Na<sub>2</sub>CO<sub>3</sub>-NaHCO<sub>3</sub>-H<sub>2</sub>O pri 50 °C [Phase equilibria in Na<sub>2</sub>SO<sub>4</sub>-Na<sub>2</sub>CO<sub>3</sub>-NaHCO<sub>3</sub>-H<sub>2</sub>O system at 50 °C]. *Vestnik Tadjikckogo natsional' nogo universiteta (seriya estesvennikh nauk) [Bulletin of the Tajik National University (series of natural sciences)]*. 2016;1(3):200. Russian.
5. Spravochnik eksperimental'nykh dannykh po rastvorimosti mnogokomponentnykh vodno-solevykh system [Reference book on experimental data for solubility in multicomponent water-salt systems]. Vol. 1. Saint-Petersburg: Khimizdat, 2003. 1151 p. Russian.
6. Spravochnik eksperimental'nykh dannykh po rastvorimosti mnogokomponentnykh vodno-solevykh system [Reference book on experimental data for solubility in multicomponent water-salt systems]. Vol. II., Books. 1–2. Saint-Petersburg: Khimizdat, 2004. 1247 p. Russian.
7. Goroshchenko YaG, Soliev L, Gornikov YuI. Opredelenie polozheniya nonvariantnykh tochek na diagrammakh rastvorimosti metodom donasyshcheniya [Determination of the invariant points' positions on solubility diagrams using the presaturation method]. *Ukrainskii Khimicheskii Zhurnal [Ukrainian Journal of Chemistry]*. 1987;53(6):568–71. Russian.
8. Aleksandrova EA. Analiticheskaya khimiya [Analytical chemistry]. Moscow: Klass, 2011. 350 p. Russian.
9. Knipovich YuN, Morachevskiy YuV. Analiz mineral'novo syr'ya [Analysis of raw minerals]. Leningrad (USSR): Goskhimizdat, 1959. 947 p. Russian.
10. Orlova TN, Ganzha BB. Metody analiza i ochistki prirodnykh i stochnykh vod. Tomsk (Russia): Tomsk polytechnical university publishing house, 2007. 168 p. Russian.
11. Marakushev AA, Bobrov AV, Partsev NN, Fenogenov AN. Osnovy kristallogoptiki. Porodoobrazuyushchie mineraly. Moscow: Nauchnyy mir, 2000. 316 p. Russian.
12. Goroshchenko YaG. Masstsentricheskii metod izobrazheniya mnogokomponentnykh system [The Center of Mass Method for Multi-component Systems Imaging]. Kiev: Naukova Dumka, 1982. 264 p. Russian.