



## Research articles

Specific Heat on Single-crystalline YVO<sub>3</sub>Agustinus Agung Nugroho<sup>1\*</sup>, Thomas T. M. Palstra<sup>2</sup><sup>1</sup>Faculty of Mathematics and Natural Sciences, Institut Teknologi Bandung, Ganesha St., No. 10, Bandung, 40132 Indonesia<sup>2</sup>Zernike Institute for Advanced Materials, University of Groningen, Nijenborg 4, 9747 AG Groningen, The Netherlands

## Article info

## Keywords:

Orbital ordering  
Specific heat  
Orthovanadate  
Magnetic entropy  
Short-range interactions

## Abstract

The specific heat of single-crystalline YVO<sub>3</sub> was measured from 2 K up to 250 K at zero field. The results reveal three transitions, at around 75, 115, and 200 K. The transitions at around 115 K and 200 K show that the phase transition is of the second-order type, whereas at around 75 K, unusual features of the specific heat are found. These unusual features are attributed to the effect of a large change in the volume. The specific heat data were analyzed in terms of a lattice contribution, a Schottky contribution and an excess magnetic contribution at high temperature. The magnetic contribution well above the magnetic ordering temperature is ascribed to short-range interactions due to the presence of strong magnetocrystalline anisotropy. The magnetic entropy considered by using this approach is 9.13 J/mole K which is close to the theoretical estimate for the  $S = 1$  system.

## 1. Introduction

The RVO<sub>3</sub> compounds (with R is rare earth element) have become an interesting series of compounds since the discovery of an anomalous diamagnetism in LaVO<sub>3</sub>. The anomalous diamagnetism occurs when the magnetization reverses its direction with respect to the applied magnetic field below the antiferromagnetic ordering. In contrast to a previous study on polycrystalline material [1], single-crystalline YVO<sub>3</sub> has shown a sign reversal magnetization [2]. Sign reversals of the magnetization occur at around 95 K and 77 K. These temperatures will be denoted as  $T^*$  and  $T_s$ , respectively. Both temperatures are below the long-range canted antiferromagnetic ordering temperature  $T_N \sim 116$  K. In this compound, the sign reversal of the magnetization is observed both in ZFC and in FC samples. Another remarkable transition in single crystalline YVO<sub>3</sub> is found at 200 K. This salient transition in the magnetic susceptibility occurs as a change in the Curie-Weiss slope resulting in a change of the effective moment from 2.81  $\mu_B$  above 200 K to 2.31  $\mu_B$  below 200 K [3]. A structural phase transition at that temperature has also been observed in X-ray as well as in neutron powder diffraction studies. Recently, a forbidden reflection in the  $Pbnm$  symmetry has been found below 200 K in synchrotron X-ray single crystal diffraction [4] and in optical studies showing a lowering of the symmetry [5].

This report is a detailed description of the specific heat result reported in Ref. 4. The specific heat data of the single-crystalline sample, which are different from the data for a polycrystalline sample [6], will be presented. We obtain a consistent magnetic entropy for  $S = 1$  using Schottky analysis. This method might be applied to obtain the magnetic contribution to the specific heat in transition metal oxide compounds.

## 2. Experimental Methods


The specific heat of single-crystalline YVO<sub>3</sub> was measured at constant pressure by using two different experimental systems and two different samples. The samples, typically rectangular, with the weight of 158.34 mg and 50.33 mg, were labeled as sample A and sample B, respectively. Sample A was measured by using a semiadiabatic method in a home-made specific heat equipment [6]. In this setup, the measurement can only be run automatically during warming up the sample. Unfortunately, it is found that upon heating above 75 K, the heat contact between the sample and the holder was lost. Having this constraint, the measurement was performed only in the temperature range from 100 to 250 K. The other sample, sample B, was measured by using a relaxation method in a commercial Quantum Design PPMS. This apparatus can be run automatically with heating and cooling mode. In this setup, the experiment was performed in the temperature range from 2 to 250 K. In order to refine the data at low temperature below 100 K, the experiments were repeated several times above and below 75 K. A reasonably good thermal contact between the sample and the holder can be achieved by a rapid quenching or warming across the transition temperature at around 75 K.

## 3. Results and Discussion

The temperature dependence of the specific heat for single-crystalline YVO<sub>3</sub> is presented in Fig. 1. The data have been corrected for the addenda. Both sample A and sample B show a good reproducibility for the peaks at around 200 K,  $T_0$ , and 115 K,  $T_N$ . In a polycrystalline sample, aside from the magnetic transition,  $T_N$ , at 116 K, Borukhovich *et al.* had observed only the transition at 77 K,  $T_s$  [7]. In contrast to that, the single-crystalline specific heat data clearly reveal three transitions. Two transitions, at  $T_0$  and  $T_N$ , are in agreement with the previous measurements of the magnetization and the crystallographic structure. These results confirm that both transitions are of the second-order type. A discrepancy, however, is found for the transition at  $T_s$ , around 75 K. A first-order transition observed as a discontinuation in the magnetization as well as in lattice parameters at  $T_s$  is not corroborated by the appearance of a sharp peak in the specific heat measurement. Instead, a jump in the specific heat is found, which indicates that the transition is of a second-order type. This discrepancy might be attributed to the inappropriate temperature step in measurement compared with the width of the transition. It is known that at  $T_s$ , the  $a$  axis and  $c$  axis increase by around 1% and 2%, respectively, while the  $b$  axis decreases by about 3%. Overall, this gives rise to a volume compression of about 1% [4]. In the series of measurements, the heat contact between the sample and the holder becomes worse at lowering the temperature, or it can totally be lost at increasing temperature while passing  $T_s$ . This effect may arise from less accuracy of the measurement around the transition. It is also found that the sample can even be broken by clamping the sample to the holder. In order to be able to obtain more information around the first-order transition, a powder measurement is suggested. In the powder sample, it is expected that there will be more degree of freedom in releasing the strain force, as shown in Ref. 4.

\*Corresponding author

Email: [nugroho@fi.itb.ac.id](mailto:nugroho@fi.itb.ac.id)



**Fig. 1.** The temperature dependence of the specific heat of the single-crystalline  $\text{YVO}_3$  from 2 to 250 K. Sample B and sample A are plotted by the  $\diamond$  and  $\circ$  symbol, respectively. The inset figure is the specific heat jump at around 75 K with a thermal hysteresis of about 0.9 K.


The temperature dependence of the specific heat is analyzed in terms of the lattice contribution,  $C_{lat}$ , the electronic Schottky contribution,  $C_{sch}$ , and the excess specific heat,  $\Delta C$ , as shown in Eq. 1.

$$C(T) = C_{lat}(T) + C_{sch}(T) + \Delta C(T). \quad (1)$$

As a first approximation, the lattice contribution at low temperature is described by the Debye approximation,  $C_{lat} = \alpha T^3$ . The coefficient  $\alpha$  is determined from the slope in the  $C/T^2$  vs  $T$  plot. It is found that the curve starts to deviate from the linear dependency above 40 K. The Debye temperature of 460 K is obtained by fitting the data below 40 K using a Debye function. It is obvious that above 40 K, the  $C_{lat}$  starts to overwhelm the experimental data. This indicates that the Debye approximation, which considers only the acoustic mode of the phonons, is insufficient to describe the lattice specific heat. In order to have a better description for the lattice contribution, the optical mode has to be included. The contribution of the optical mode can be considered by using an Einstein function. The  $C_{lat}$  is, therefore, expressed in a hybrid Debye-Einstein model [8], as shown in Eq. 2:

$$C_{lat}(T) = \alpha_D D(\theta_D/T) + \alpha_E E(\theta_E/T) \quad (2)$$

where  $D(\theta_D/T)$  and  $E(\theta_E/T)$  are Debye and Einstein functions, respectively. The Debye temperature,  $\theta_D$ , is fixed at 460 K, while the Einstein temperature,  $\theta_E$ , of 800 K is adopted from one of the oscillators used in the  $\text{YMnO}_3$  compound [9]. The coefficient  $\alpha_D$  of 2/3 and  $\alpha_E$  of 1/3 are obtained by extrapolating the low-temperature data to the high-temperature data. The result of this extrapolation is shown in Fig. 2.




**Fig. 2.** The temperature dependence of the specific heat from 2 to 250 K. The continuous line and the dashed-line are the Schottky contribution and the lattice contribution, respectively.

Another important contribution to the specific heat data is given by the electronic Schottky term. It is mentioned earlier that the low energy levels of  $\text{YVO}_3$  consist of a singlet ground state and a doublet excited state. This scheme can be described by a two-level Schottky contribution as presented in Eq. 3:

$$C_{sch} = R \left(\frac{\Delta}{T}\right)^2 \frac{g_0}{g_1} \frac{\exp(\Delta/T)}{\left(1 + \frac{g_0}{g_1} \exp(\Delta/T)\right)^2} \quad (3)$$


with  $g_0$  and  $g_1$  are the degeneracies of the ground state and the excited state, respectively.  $\Delta$  is the energy separation between the two levels. The ratio,  $g_0/g_1$ , and the energy separation,  $\Delta$ , are taken as free parameters to fit the data below 30 K and the data ranging from 75 to 80 K in the  $C$  vs  $T$  plot. The best fit is provided by the parameters  $g_0/g_1 = 0.51$  and  $\Delta = 196$  K. These parameters are in agreement with the theoretical prediction for the two-level state, with the energy separation of about 200 K. The result of this fitting is depicted in Fig. 2. It is interesting to note that the Schottky contribution from 30 to 75 K gives a smooth extrapolation curve in the total specific heat, as shown in Fig. 2. The smooth extrapolation points below the magnetic transition turn out to be a bump in the  $C/T$  curve after subtracting the lattice contribution, as displayed in Fig. 3. A bump feature has recently been reported as well for the manganese oxides, i.e., for  $\text{YMnO}_3$ ,  $\text{LuMnO}_3$ , and  $\text{ScMnO}_3$  [10]. The Schottky

analysis considering the bump feature in those compounds has not yet been carried out. In spite of the fact that the bump feature is absent experimentally in  $\text{YVO}_3$ , the electronic scheme allows the consideration of a Schottky contribution to its specific heat.



**Fig. 3.** The temperature dependence of the specific heat plotted as  $C/T$  after subtracting the lattice contribution. The continuous line and the dashed-line are the Schottky contribution and the extrapolation data, respectively.

It is known that  $\text{YVO}_3$  has a strong magnetocrystalline anisotropy already above  $T_N$  [3]. It is, therefore, expected that the short-range interactions are already present above a long-range magnetic ordering. In order to take into account this effect, an extrapolation is made for the data above  $T_N$  to the Schottky “tail” at high temperature; presumably, the magnetic specific heat at high temperature is given only by the Schottky contribution. The extrapolation points, which are the excess of magnetic specific heat above the magnetic ordering,  $\Delta C_M$ , are plotted in Fig. 3. For further analysis, two types of data sets are assembled, as displayed in Fig. 4(a). Both data set consist of the extrapolation points  $\Delta C_M$  above 120 K. Below 120 K, one of the data set include the Schottky contribution or bump while the other data set remain as the experimental data. These data are called data-1 and data-2, respectively, hereafter.



**Fig. 4.** (a) The temperature dependence of the specific heat after subtracting the lattice contribution for (1) the experimental data and (2) the Schottky contribution, below 120 K. Above 120 K, both (1) and (2) are given by the extrapolation data  $\Delta C_M$ . (1) and (2) in figure (b) are the temperature dependence of the magnetic entropy for data (1) and (2) described in figure (a). The average value between (1) and (2) above  $T_N$  is plotted in (3).

The magnetic entropy calculated by the numerical integration between 10 and 250 K of those data sets is displayed in Fig. 4(b). The total magnetic entropy obtained from the data-1 is 8.38 J/mole K. This value is smaller compared to the theoretical estimation. Theoretically, the expected total magnetic entropy is given by the  $\text{V}^{3+}$  ion with total spin  $S=1$ , i.e.,  $S = R \ln(3) = 9.13$  J/mole K. Meanwhile, the magnetic entropy obtained from the data-2 is 9.88 J/mole K, and the average magnetic entropy obtained from the data-1 and data-2 is about the theoretical value. This demonstrates that the loss of entropy in data-1 is possibly due to the local effect in the electronic structure (reoccupation of the  $d_{xz}$  and  $d_{yz}$  orbitals) at the first-order transition. This finding is compatible with the observed change of the orbital ordering and the Jahn-Teller distortion at the first order transition discussed earlier. This local effect might also be the reason for the small change of the magnetic entropy at the  $T_s$  as shown in Fig. 4(b).

Turning our attention to the transition at around 200 K,  $T_0$ , the peak in the specific heat data at this temperature confirms that the change in the crystallographic structure, from orthorhombic ( $Pbnm$ ) to monoclinic ( $P2_1/a$ ) with an a-type Jahn-Teller distortion, is of a second-order type. This transition was not observed in the specific heat measurement in a polycrystalline sample [7]. Besides a change in slope of the inverse magnetic susceptibility [3] and of the lattice parameters observed by the X-ray powder diffraction, which were observed previously, the recent synchrotron X-ray single crystal diffraction [4], as well as the infrared spectroscopy, are able to detect the lowering of  $Pbmn$  symmetry [5] at  $T_0$ . While the synchrotron X-ray detects an emerge of the forbidden reflection for  $Pbmn$  symmetry as lowering temperatures below  $T_0$ , the infrared spectroscopy detects new modes from the infrared active. An evidence for the orbital ordering in  $\text{YVO}_3$  has recently been reported by means of the crystallographic studies [4] similar to those for the  $\text{LaMnO}_3$  [11] and resonance inelastic X-ray scattering study [12]. The change in the crystallographic structure at  $T_0$ , as described earlier has provided evidence of the onset of the orbital ordering.

Figure 5 shows the specific heat between 130 and 250 K after subtracting the lattice contribution, the Schottky contribution and the excess of the magnetic specific heat. The total entropy, obtained by numerical integration in this temperature range, is 2.44 J/mole K. Since there are three types of  $d$  orbitals involved under this consideration; therefore a rough estimate of the orbital entropy is given by  $R \ln(3) = 9.13$  J/mole K. The experimental value is too small in comparison to this estimate. This discrepancy should be a subject for further investigation, besides a comparison of the orbital entropy in the different perovskite system.




Fig. 5. The temperature dependence of the specific heat from 120 to 250 K after subtracting the  $C_{lat}$ ,  $C_{sch}$ , and  $\Delta C_M$ . The continuous line is the entropy obtained from the specific heat at this temperature range.

#### 4. Conclusions

We have presented the preparation of single-crystalline  $YVO_3$  by using the TSFZ technique and its characterization.  $YVO_3$  is unique among the transition metal oxides. It exhibits a peculiar interplay between the crystal structure, orbital ordering, and spin ordering. Besides a well-known second order type of antiferromagnetic transition at around 115 K, the result from the specific heat has established that there is a phase transition at 200 K with a nature of second order type. At around 75 K,  $T_S$ , the specific heat shows an unusual feature that can not be described with a common expectation for the type of phase transition. Experimentally, the effects of the structural transition at 75 K are ascribed to the uncertainty of the data around this transition. The amount of magnetic entropy which is analyzed by including the Schottky contribution shows a small loss of magnetic entropy. This loss is due to a local effect in the change of the electronic structure around  $T_S$ .

#### Acknowledgements

We acknowledge support from Alois Menovsky, Jaap Franse for guiding the research and Yuri Jansen for handling the glass cryostat for specific heat measurement at van der Waals-Zeeman Institute, University of Amsterdam, The Netherlands, in the year 2000. T.T.M. Palstra is currently at Solid State Chemistry Group, University of Twente, The Netherlands.

#### References

- [1] H. C. Nguyen and J. B. Goodenough, "Magnetic studies of some orthovanadates," *Phys. Rev. B*, vol. 52, no. 1, pp. 324–334, Jul. 1995, doi: 10.1103/PhysRevB.52.324.
- [2] Y. Ren, T. T. M. Palstra, D. I. Khomskii, E. Pellegrin, A. A. Nugroho, A. A. Menovsky, and G. A. Sawatzky, "Temperature-induced magnetization reversal in a  $YVO_3$  single crystal," *Nature*, vol. 396, no. 6710, pp. 441–444, Dec. 1998, doi: 10.1038/24802
- [3] Y. Ren, T. T. M. Palstra, D. I. Khomskii, A. A. Nugroho, A. A. Menovsky, and G. A. Sawatzky, "Magnetic properties of  $YVO_3$  single crystals," *Phys. Rev. B*, vol. 62, no. 10, p. 6577, Sep. 2000, doi: 10.1103/PhysRevB.62.6577
- [4] G. R. Blake, T. T. M. Palstra, Y. Ren, A. A. Nugroho, and A. A. Menovsky, "Transition between orbital orderings in  $YVO_3$ ," *Phys. Rev. Lett.*, vol. 87, no. 24, p. 245501, Oct. 2001, doi: 10.1103/PhysRevLett.87.245501
- [5] A. A. Tsvetkov, F. P. Mena, Y. Ren, I. S. Elfimov, P. H. M. Van Loosdrecht, D. Van Der Marel, A. A. Nugroho, A. A. Menovsky, and G. A. Sawatzky, "Optical and magneto-optical study of orbital and spin ordering transitions in  $YVO_3$ ," *Physica B: Condensed Matter*, vol. 312–313, pp. 783–784, Mar. 2002, doi: 10.1016/S0921-4526(01)01494-6
- [6] N. H. Kim-Ngan, "Magnetic Phase Transitions in  $NdMn_2$  and Related Compounds," Universiteit van Amsterdam, 1993.
- [7] A. S. Borukhovich, G. V. Bazuev, G. P. Shvikin, "Specific heat and magnetic phase in  $LaVO_3$ ," *Sov. Phys. Solid State*, vol. 16, p. 191, 1974.
- [8] B. F. Woodfield, J. L. Shapiro, R. Stevens, J. Boerio-Goates, and M. L. Wilson, "Critical phenomena at the antiferromagnetic transition in  $MnO$ ," *Phys. Rev. B*, vol. 60, no. 10, pp. 7335–7340, Sep. 1999, doi: 10.1103/PhysRevB.60.7335.
- [9] A. Muñoz, J. A. Alonso, M. J. Martínez-Lope, M. T. Casáis, J. L. Martínez, and M. T. Fernández-Díaz, "Magnetic structure of hexagonal  $RMnO_3$  ( $R = Y, Sc$ ): Thermal evolution from neutron powder diffraction data," *Phys. Rev. B*, vol. 62, no. 14, pp. 9498–9510, Oct. 2000, doi: 10.1103/PhysRevB.62.9498.
- [10] D. G. Tomuta, S. Ramakrishnan, G. J. Nieuwenhuys, and J. A. Mydosh, "The magnetic susceptibility, specific heat and dielectric constant of hexagonal  $YMnO_3$ ,  $LuMnO_3$  and  $ScMnO_3$ ," *J. Phys. Condens. Matter*, vol. 13, no. 20, pp. 4543–4552, May 2001, doi: 10.1088/0953-8984/13/20/315.
- [11] Rodríguez-Carvajal, M. Hennion, F. Moussa, A. H. Moudden, L. Pinsard, and A. Revcolevschi, "Neutron-diffraction study of the Jahn-Teller transition in stoichiometric  $LaMnO_3$ ," *Phys. Rev. B*, vol. 57, no. 6, pp. R3189–R3192, Feb. 1998, doi: 10.1103/PhysRevB.57.R3189.
- [12] E. Benckiser, L. Fels, G. Ghiringhelli, M. Moretti Sala, T. Schmitt, J. Schlappa, V. N. Strocov, N. Mufti, G. R. Blake, A. A. Nugroho, A. A. T. T. M. Palstra, M. W. Haverkort, K. Wohlfeld, and M. Grüninger, "Orbital superexchange and crystal field simultaneously at play in  $YVO_3$ : Resonant inelastic x-ray scattering at the v L edge and the O K edge," *Phys. Rev. B*, vol. 88, p. 205115, Nov. 2013, doi: 10.1103/PhysRevB.88.205115.